

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	7548	(polyolefin or ethylene near propylene or styrene near butadiene) and styrene near butadiene and (\$6phenylenediamine)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:40
L2	4002	(polyolefin or ethylene near propylene or styrene near butadiene) and styrene near butadiene and (\$6phenylenediamine) and (melt \$6 or molt\$4)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:41
L3	3830	copolymer and (polyolefin or ethylene near propylene or styrene near butadiene) and styrene near butadiene and (\$6phenylenediamine) and (melt \$6 or molt\$4)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:41
L4	3218	copolymer near4 (polyolefin or ethylene near propylene or styrene near butadiene) and styrene near butadiene and (\$6phenylenediamine) and (melt \$6 or molt\$4)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:41
L5	1183	copolymer near4 (polyolefin or ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt\$6 or molt\$4)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:42
L6	1183	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:42
L7	327	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:43
L8	2	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and commingle\$4	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:44

L9	15343	commingle\$4	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:44
L10	322	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and blend\$4	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:47
L11	1038	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and blend\$4	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:47
L12	229	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and blend\$4 and tensile near strength	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:48
L13	229	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and blend\$4 and tensile near strength	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 16:48
L14	163	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and blend\$4 and tensile near strength and (knead\$4 or extrud \$4)	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 17:07
L15	71	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and blend\$4 and tensile near strength and (knead\$4 or extrud \$4)	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 17:08

L16	71	copolymer near4 (ethylene near propylene or styrene near butadiene) and styrene near butadiene near10 block and (\$6phenylenediamine) and (melt \$6 or molt\$4) and recycl\$4 and blend\$4 and tensile near strength and (knead\$4 or extrud \$4) and (molecular near weight or mw)	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 17:12
L17	0	"4212789" and screw	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 17:59
L18	0	"4212789" and \$4screw	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 17:59
L19	3	"4212789" and \$4extrud\$4	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 17:59
L20	3	"4212789" and quinone	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 18:03
L21	8	quinone/.ttl. and phenylenediamine	USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 18:04
L22	15	quinone/.ttl. and phenylenediamine	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/04/06 18:06

4/ 6/ 2009 6:43:23 PM

C:\Documents and Settings\boykin\My Documents\EAST\Workspaces\Default EAST Workspace (Flat Panel LANDSCAPE).wsp